
Report on the synthesis of a lubricant sample (REF SPC 93-4036)

Prof. R.D. Chambers & Dr. M.P. Greenhall, University of Durham, UK.

(This report completes the second agreement)

September 21, 1993



19961113 150

# DISCLAIMER NOTICE



THIS DOCUMENT IS BEST QUALITY AVAILABLE. THE COPY FURNISHED TO DTIC CONTAINED A SIGNIFICANT NUMBER OF PAGES WHICH DO NOT REPRODUCE LEGIBLY.

REPORT DO	CUMENTATION PAG	Form Approved OMB No. 0704-0188			
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.					
AGENCY USE ONLY (Leave blank)		3. REPOR	RT TYPE AND DATES C	OVERED	
	21 September 1993	Final Repo	rt		
4. TITLE AND SUBTITLE			5. FUND	NG NUMBERS	
Report on the Synthesis of a Lubricant Sample				F6170893W0654	
6. AUTHOR(S)					
Prof R.D.Chambers and Dr.M.P.Greenhall					
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)				ORMING ORGANIZATION RT NUMBER	
University of Durham Dept of Chemistry, Science Laboratories South Road				SPC-93-4036	
Durham DH1 3LE, England					
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				ISORING/MONITORING NCY REPORT NUMBER	
EOARD PSC 802 BOX 14			Adel	SPC-93-4036	
FPO 09499-0200					
11. SUPPLEMENTARY NOTES					
			L 40% DIOT	TO DE LA CORPE	
12a. DISTRIBUTION/AVAILABILITY STATEMENT			120. DIST	12b. DISTRIBUTION CODE	
Unlimited					
13. ABSTRACT (Maximum 200 words)					
The objective of this project was to further develop the techniques associated with the preparation of samples of substituted perfluoropolyethers, including the preparation of a 10 to 20 gram sample of perfluoropolyether for lubricant testing by the USAF.					
the preparation of a 10 to 20 grain sample of perhapsolycitics for abhoratic testing by the 60% in .					
DIEC QUALITY INSPECTED &					
				Las NUMBER OF BACES	
14. SUBJECT TERMS				15. NUMBER OF PAGES	
				10 16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT	18. SECURITY CLASSIFICATION OF THIS PAGE	19, SECURITY ( OF ABSTRA	CLASSIFICATION ACT	20. LIMITATION OF ABSTRACT	
UNCLASSIFIED	UNCLASSIFIED	UNC	LASSIFIED	UL	

### Introduction

The objective of this project was to further develop the techniques associated with the preparation of samples of substituted perfluoropolyethers, including the preparation of a 10 to 20 gram sample of perfluoropolyether (1) for lubricant testing by the USAF.

 $(n=ca~22,~n\hbox{-}x=ca~13) \label{eq:cf3} (R_F=CF_3CF_2CF_2,~R'_F=R_F~(predom)~or~F,~~all~unmarked~bonds~to~F)$ 

(Note: Chambers, US Patent 4,877,905)

### **Experimental**

## a) Starting materials

Dimethylpolyethylene glycol(1000)  $\{n = 22.3\}$  was supplied by Merck-Schuchardt, ditertiarybutylperoxide was supplied by Aldrich Chemical Company Limited. Hexafluoropropene was supplied by Fluorochem Limited. 50% Fluorine/Nitrogen mixture was supplied by Air Products.

# b) Reaction of Dimethylpolyethylene glycol (2) with hexafluoropropene

Into a 300ml stirred autoclave was introduced (2) (94.0g, 0.91 moles), and ditertiary butyl peroxide (6.3g, 0.043 moles). Dissolved oxygen was removed by introducing high pressure nitrogen gas (15 Bar), stirring, and carefully venting (repeated twice). The autoclave system was then evacuated. Hexafluoropropene gas (ca 10g) was introduced and the autoclave was heated to 130°C with stirring. Hexafluoropropene was then allowed to pressurise the autoclave from a room temperature cylinder. The autoclave contents were heated to and then maintained at a temperature of 140°C for ca 2 hours until the uptake of hexafluoropropene gas had ceased. This procedure was repeated with fresh initiator four times, taking samples each time. Finally a portion of product with fresh initiator (6.7g) was reacted further with hexafluoropropene. The autoclave contents were heated to 140°C during which time the internal pressure rose to ca 20 Bar. After stirring for a period of 2.5 hours the autoclave was cooled and opened. N.M.R. analysis of the stripped product (an orange oil) (3) indicated that there were ca 15.5 hexafluoropropyl groups per polyethylene glycol molecule.

### c) Reaction of (3) with fluorine/nitrogen mixtures

Y 
$$F_2/N_2$$
 Y  $F_2/N_2$  Y  $F_$ 

A solution of (3) (21.3g) in (4) (99.9g) was introduced into a stirred FEP reaction vessel. A F2/N2 mixture containing initially 5% F<sub>2</sub> rising to 50% F<sub>2</sub>, was passed into the vessel at room temperature. When the reactivity had decreased the mixture was transferred into an FEP tube through which 50% F2/N2 was bubbled. At this time ca 59% of the hydrogen atoms had been replaced by fluorine. Perfluorination was effected by passing 50% F2/N2 through the mixture under ultra violet irradiation (100W then 1000W). The volatile, now perfluorinated, solvent (85g) was removed under reduced pressure (150°C, <1mmHg) leaving a colourless viscous oil (16g) (1). A small quantity of higher molecular weight solid polyether was also obtained (ca 0.7g). Many n.m.r. samples were removed during fluorination to monitor the process, hence, the weight of the final product does not reflect the efficiency of the process. A sample of (1) (12.0g) was sealed into two evacuated ampoules (2 of 6g) and dispatched to A. Davison, Euro, Off. Aerospace R+D (AFSC), 223/231 Old Marylebone Road, London NW1 5TH for forwarding to Wayne Ward at Wright Patterson AFB, Ohio.

### Characterisation of Intermediates/Products

### Estimation of degree of hexafluoropropene incorporation

To an n.m.r. sample (CDCl<sub>3</sub> as solvent) was added 1 to 4 drops of  $\alpha,\alpha,\alpha$ -trifluorotoluene. By determining the ratio of high field <sup>1</sup>H & <sup>19</sup>F n.m.r. integrals of the sample and trifluorotoluene it was possible to assess the extent of hexafluoropropene incorporation.

### Estimation of degree of fluorination

To an n.m.r. sample (CDCl<sub>3</sub> as solvent in early stages of fluorination, neat in later stages) was added 1 to 4 drops of  $\alpha,\alpha,\alpha$ -trifluorotoluene. By determining the ratio of high field <sup>1</sup>H & <sup>19</sup>F n.m.r. integrals of the sample and trifluorotoluene it was possible to assess the extent of fluorination knowing the extent of hexafluoropropene incorporation.

<sup>19</sup>F N.M.R. of (1)

See Appendix 1 for 235MHz n.m.r. spectrum.

<sup>13</sup>C N.M.R of (1)

At 62.9MHz multiple overlapping resonances between 100 and 125 ppm.

Elemental Analysis of (1)

Elemental analysis indicated 0.0% Hydrogen and 22.7% Carbon.

### <u>Summary</u>

A perfluorinated polyether of novel structure has been produced. Aspects of the larger scale synthesis of such materials have been developed. We look forward to further development of syntheses of new materials of novel structure, for testing as lubricants in arrangement with Wright Patterson AFB, Ohio, USA.

